

T H E H A R R I S P R O D U C T S G R O U P A L I N C O L N E L E C T R I C C O M P A N Y 4501 Quality Place • Mason, OH 45040 U.S.A Tel: 513-754-2000 Fax: 513-754-6015

TECHNICAL SPECIFICATION SHEET

ER 80S-D2 CR-MO WELDING WIRE

STATEMENT OF LIABILITY- DISCLAIMER

Any suggestion of product applications or results is given without representation or warranty, either expressed or implied. Without exception or limitation, there are no warranties of merchantability or of fitness for particular purpose or application. The user must fully evaluate every process and application in all aspects, including suitability, compliance with applicable law and non-infringement of the rights of others. The Harris Products Group and its affiliates shall have no liability in respect thereof.

APPLICATION:

80S-D2 contains molybdenum for increased strength and manganese and silicon as a de-oxidizer helping to control porosity when welding with CO₂. The weld deposit yields excellent quality and bead appearance on carbon and low-alloy steels; also may be used for out-of position with short circuiting and pulsed arc process. Use with a preheat and interpass temperature of 275°f minimum.

NOMINAL CHEMICAL COMPOSITION:

Phosphorus	.025% max	Carbon	.0712%
Copper	.50% max	Manganese	1.60-2.10%
Other Totals	.50 % max	Sulfur	.025% max
Nickel	.15% max	Silicon	.5080%
Iron	Balance	Molybdenum	.4060%

TYPICAL MECHANICAL PROPERTIES AS WELDED:

(Properties are greatly influenced by the preheat, inter-pass and post-heat used)

Tensile Strength (psi) 84,000 Impact Strength @120°F 35 ft-lbs

Elongation % in 2" 19% Yield Strength (psi) 71,500

* RECOMMENDED WELDING PARAMETERS:

GMAW(MIG) Parameters (DC Reverse Polarity) Electrode Positive Spray transfer

Wire Diameter	<u>AMPS</u>	<u>VOLTS</u>	(3) CO ₂ /AR-CO ₂ (cfh)	Wire Feed imp
.023	30-90	14-19	20-25	100-400
.030	40-145	15-21	20-25	160-380
.035	50-180	16-22	20-25	150-340
.045	75-250	17-22	20-25	100-220

⁽³⁾ Setting based on CO₂ for mild steel, Ar-CO₂ for low alloy steel

GMAW(MIG) Parameters(DC Reverse Polarity) Electrode Positive short-circuiting

GTAW (Tig) Parameters (DCSP) 2 %Thoriated Tungsten Electrode negative (1)

<u>Material</u>	Tungsten dia. (1)	Filler Wire Size	<u>Amps</u>	Gas Cup	Argon (cfh)
1/16"	1/16"	1/16"	100-140	3/8	20
3/32"	1/16"	1/16"	100-160	3/8	20
1/8″	3/32"	1/16"	125-200	7/16	20
3/16"	3/32"	3/32"	150-250	7/16	25
1/4"	1/8"	1/8″	150-250	1/2	25
3/8"	1/8"	1/8″	150-275	1/2	25
1/2"	1/8″	1/8″	150-300	1/2	25

All statements, information and data given are believed to be accurate and reliable but are presented without guarantee, warranty or responsibility of any kind, expressed or implied.

Additional information available at our web site: www.harrisproductsgroup.com



* All parameters are suggested as basic guidelines and will vary depending on joint design number of passes , and other factors .

SPECIFICATION COMPLIANCE: AISI/AWS A5.28 & ASME SFA 5.28 ER 80S-D2

WARNING: PROTECT yourself and others. Read and understand this information.

FUMES AND GASES can be hazardous to your health.

ARC RAYS can injure eyes and burn skin.

ELECTRIC SHOCK can KILL.

- Before use, read and understand the manufacturer's instructions, Material Safety Data Sheets (MSDS), and your employer's safety practices.
- Keep your head out of fumes.
- Use enough ventilation, exhaust at the arc, or both, to keep fumes and gases from your breathing zone and the general area.
- Wear correct eye, ear, and body protection.
- Do not touch live electrical parts.
- See American National Standard Z49.1, Safety in Welding, Cutting, and Allied Processes, published by the American Welding Society, 550
 N.W. LeJeune Road, Miami, Florida 33126; OSHA Safety and Health Standards, available from the U.S. Government Office, Washington, DC 20402